

(12) **EUROPEAN PATENT SPECIFICATION**

- (45) Date of publication of patent specification: 04.01.84 (51) Int. Cl.³: G 03 C 1/68, G 03 C 1/72
(21) Application number: 80104770.5
(22) Date of filing: 12.08.80

(54) Photoimaging composition comprising a 2,4,5-triphenylimidazolyl dimer and at least one compound selected from the group consisting of a leuco dye and a polymerizable ethylenically unsaturated monomer.

(30) Priority: 14.08.79 US 66373

(43) Date of publication of application:
11.03.81 Bulletin 81/10

(45) Publication of the grant of the patent:
04.01.84 Bulletin 84/1

(84) Designated Contracting States:
BE CH DE FR GB LI

(56) References cited:
FR - A - 2 089 284
US - A - 3 390 994
US - A - 3 445 234
US - A - 3 479 185
US - A - 3 615 481
US - A - 3 658 543
US - A - 3 784 557

(73) Proprietor: E.I. DU PONT DE NEMOURS AND
COMPANY
Legal Department 1007 Market Street
Wilmington Delaware 19898 (US)

(72) Inventor: Dessauer, Rolf
P.O. Box 3796
Greenville Delaware 19807 (US)

(74) Representative: Werner, Hans-Karsten, Dr. et al,
Deichmannhaus am Hauptbahnhof
D-5000 Köln 1 (DE)

EP O 024 629 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European patent convention).

Photoimaging composition comprising a 2,4,5-triphenylimidazolyl dimer and at least one compound selected from the group consisting of a leuco dye and a polymerizable ethylenically unsaturated monomer

Technical Field

This invention relates to photoimaging compositions. More particularly, it relates to photoimaging compositions containing selectively substituted 2,4,5-triphenylimidazolyl dimers.

Background Art


Photoimaging compositions utilizing substituted hexaarylbiimidazole compounds in conjunction with either a leuco dye or an ethylenically unsaturated monomer compound, as well as other additives, are known, cf. US—A—3 445 234. Such compositions are sensitive to radiation in the shorter wavelength range of the ultraviolet spectrum. For many reasons it is desirable that the spectral sensitivity of these compositions be extended into the longer wavelength range of the spectrum or the reactivity of these compositions be increased so that they can respond most efficiently to less costly lower energy light exposure sources. To accomplish this many additives have been used in conjunction with hexaarylbiimidazoles, e.g., aromatic hydrocarbons, coumarins, carbocyanine dyes, hydroxyphthalein dyes, acridine dyes, aminophenylketones, etc. The use of additives, while effective, often is not desired because not only does the presence of the specific additive increase the cost of the formulation, but it requires experimental work of skilled chemists to find additives of appropriate solubility characteristics and chemical properties to permit existence of the additive in the photoimaging composition, to develop the optimum formulations, and to maintain appropriate and effective quality control over the chosen additives. The known additives have been found to be effective in the formulations typical of substituted hexaarylbiimidazole-containing photoimaging compositions. After a period of time, however, it has been found that there may be a tendency for crystallization to occur causing an undesired decrease in photosensitivity and a discontinuity in photo-response in the areas where the crystals form.

It is desirable that the above disadvantages be overcome and that formulations be prepared containing hexaphenylbiimidazole compounds sensitive to longer wavelengths of the spectrum and having increased radical reactivity.

Disclosure of the Invention

In accordance with this invention there is provided a photoimaging composition comprising an admixture of

(A) at 2,4,5-triphenylimidazolyl dimer of the formula:



wherein

R_1 is 2-bromo, 2-chloro, 2-fluoro, 2-alkyl of 1 to 4 carbon atoms and 2,4-dichloro;

R_2 is 2-bromo, 2-chloro, 2-fluoro, 4-chloro, 2-alkyl of 1 to 4 carbon atoms, 2-cyano, and 2-alkoxy wherein the alkyl radical is of 1 to 4 carbon atoms; and

R_3 is 3,4-dimethoxy, 3,4-diethoxy, 2,3-dimethoxy, 2,4,6-trimethoxy, 4-alkoxy wherein the alkyl radical is of 1 to 4 carbon atoms and 3,4-methylenedioxy; the imidazolyl dimer having an extinction coefficient determined by methylene chloride at 10^{-5} to 10^{-3} mol/liter at 350 nm of at least 4000 liters/mol cm and at 400 nm of at least 250 liters/mol cm; and at least one compound taken from the group consisting of

(B1) a leuco dye that is oxidizable to dye by the imidazolyl radicals; and

(B2) an addition polymerizable ethylenically unsaturated monomeric compound.

The photoimaging compositions of the invention comprise the specific 2,4,5-triphenylimidazolyl

dimers and leuco dye in its leuco form, or, in the event that the composition is photopolymerizable, a compound having ethylenic unsaturation. Both the leuco dye and ethylenically unsaturated compound can be present in the composition as noted below. The photoimaging composition containing the specific 2,4,5-triphenylimidazolyl dimer and leuco dye is stabilized to prevent color build-up in the non-image areas. The following processes have been found to be effective to achieve such stabilization: treatment with solution containing a free radical trap, e.g., hydroquinone, phenidone, etc.; inclusion in the coating of precursors of hydroquinone which lead to its generation by heat, e.g., dihydropyran adduct of ditertiarybutylhydroquinone; inclusion of quinones (photoactivatable oxidants) and hydrogen donor compounds (reductant components) which may be employed to generate hydroquinones by light exposure, preferably at wavelength distinct from the colorforming exposure; and photopolymerizable compounds which act as plasticizers to promote color formation until polymerized when they limit diffusion of color forming species and prevent formation of image color. It is desirable to add to the photoimaging composition a film-forming polymeric binder. Suitable inert solvents are generally present in preparing the formulations and plasticizers are commonly used therein. Additional components which can be present include: anti-blocking agents, dyes, and white and colored pigments which do not act as sensitizers, etc.

In the photopolymerizable composition containing the specific 2,4,5-triphenylimidazolyl dimer and addition polymerizable ethylenically unsaturated compound there can be present a free radical producing, electron donor agent hydrogen donor (hydrogen donor), e.g., organic amines, mercaptans, certain halogen-containing compounds, active methylene compounds, etc. Optional components that can be present in the photopolymerizable composition are: film-forming polymeric binders, inert solvents, plasticizers, chain transfer agents, energy transfer dyes, oxygen scavengers, ultraviolet absorbers, etc. After imagewise exposure an image pattern can be observed in the photopolymerizable composition (in layer form) by toning with a colored toner or by solvent washout.

The specific 2,4,5-triphenylimidazolyl dimers useful in the photoimaging compositions are defined above. The dimers have what is classified as "intra-radical asymmetry". The selected triphenylimidazole precursor to the dimer is asymmetrical about a plane perpendicular to the plane of the triphenylimidazole molecule and bisecting the N—C—N bond angle of the formula set forth above.

This type of asymmetry is dependent on the substitution in the phenyl rings at the 4- and 5-positions on the imidazole ring. It is determined by the choice of the benzil precursor to the triphenylimidazole. Preferred compounds used in the compositions of this invention have been found to give rise to free radicals which, in the absence of leuco dyes, possess extended free radical life, i.e., show reduced tendency to recombine to give corresponding dimers. As dimerization removes reactive species, i.e., imidazolyl radicals, from the photoimaging compositions, reduced tendency to dimerize enhances imaging speed and performance. Examples 1 to 10 below illustrate the synthesis of the asymmetrical hexaphenylbiimidazoles of the invention wherein the selected benzoin and benzaldehyde are refluxed in methanol in the presence of copper acetate and ammonia, an adaptation of the procedure of Wiedenhagen et al., Ber. 70,570 (1937). Another preparation procedure involves heating a benzil and a benzaldehyde at 180° to 190°C in formamide solution as disclosed in Belgian Patent 589,417.

The specific triphenylimidazolyl dimers are present in 0.1 to 10.0 percent by weight of solids in the photoimaging compositions and 0.1 to 15.4% by weight of solids in the photopolymerizable composition.

The leuco form of the dye which comprises one component of a photoimaging composition of the present invention is the reduced form of the dye having one or two hydrogen atoms, the removal of which together with an additional electron in certain cases produces the dye. Such dyes have been described, for example, in U.S. Patent 3,445,234, column 2, line 49 to column 8, line 55. The following classes are included:

- (a) aminotriarylmethanes
- (b) aminoxanthenes
- (c) aminothioxanthenes
- (d) amino-9,10-dihydroacridines
- (e) aminophenoxazines
- (f) aminophenothiazines
- (g) aminodihydrophenazines
- (h) aminodiphenylmethanes
- (i) leuco indamines
- (j) aminohydrocinnamic acids (cyanoethanes, leuco methines)
- (k) hydrazines
- (l) leuco indigoid dyes
- (m) amino-2,3-dihydroanthraquinones
- (n) tetrahalo-p,p'-biphenols
- (o) 2(p-hydroxyphenyl)-4,5-diphenylimidazoles
- (p) phenethylanilines

Of these leuco forms, (a) through (i) form the dye by losing one hydrogen atom, while the leuco forms (j) through (p) lose two nitrogen atoms to produce the parent dye. Aminotriarylmethanes are preferred. A general preferred aminotriarylmethane class is that of the acid salts of aminotriarylmethanes wherein at least two of the aryl groups are phenyl groups having (a) an R_1R_2N -substituent in the position para to the bond to the methane carbon atom wherein R_1 and R_2 are each groups selected from hydrogen, C_1 to C_{10} alkyl, 2-hydroxyethyl, 2-cyano-ethyl, or benzyl and (b) a group ortho to the methane carbon atom which is selected from lower alkyl (C is 1 to 4), lower alkoxy (C is 1 to 4), fluorine, chlorine or bromine; and the third aryl group may be the same as or different from the first two, and when different is selected from

(a) Phenyl which can be substituted with lower alkyl, lower alkoxy, chloro, diphenylamino, cyano, nitro, hydroxy, fluoro or bromo;

(b) Naphthyl which can be substituted with amino, di-lower alkylamino, alkylamino;

(c) Pyridyl which can be substituted with alkyl;

(d) Quinoly;

(e) Indolinylidene which can be substituted with alkyl.

Preferably, R_1 and R_2 are hydrogen or alkyl of 1—4 carbon atoms. Leuco dye is present in 0.1 to 5.0 percent by weight of solids in the photoimaging composition.

With the leuco form of dyes which have amino or substituted amino groups within the dye structure and which are characterized as cationic dyes, an amine salt-forming mineral acid, organic acid, or an acid from a compound supplying acid is employed. The amount of acid usually varies from 0.33 mol to 1 mol per mol of amino nitrogen in the dye. The preferred quantity of acid is about 0.5 to 0.9 mol per mol of amino nitrogen. Representative acids which form the required amine salts are hydrochloric, hydrobromic, sulfuric, phosphoric, acetic, oxalic, p-toluenesulfonic, trichloroacetic, trifluoroacetic and perfluoroheptanoic acid. Other acids such as acids in the "Lewis" sense or acid sources which may be employed in the presence of water or moisture include zinc chloride, zinc bromide, and ferric chloride. Representative leuco dye salts include tris- (4-diethylamino-o-tolyl) methane zinc chloride, tris- (4-diethylamino-o-tolyl) methane oxalate, tris- (4-diethylamino-o-tolyl) methane p-toluene-sulfonate and the like.

The redox couple useful in the photoimaging composition is described in U.S. Patent 3,658,543, column 9, lines 1 to 46. Preferred oxidants include 9,10-phenanthrenequinone alone or in admixture with 1,6- and 1,8-pyrenequinone which absorb principally in the 430 to 550 nm region. The reductant component of the redox couple is 100 to 10 percent of an acyl ester of triethanolamine of the formula:



where R is alkyl of 1 to 4 carbon atoms, and 0 to 90 percent of a C_1 to C_4 alkyl ester of nitrilotriacetic acid or of 3,3',3''-nitrilotripropionic acid. Triethanolamine triacetate and dibenzylethanolamine acetate are preferred reductant components. The molar ratios of oxidants to biimidazole used ranges from 0.01:1 to 2:1, preferably 0.2:1 to 0.6:1. The molar ratios of reductant to biimidazole used ranges from about 1:1 to about 90:1, preferably 10:1 to 20:1.

Optionally, other additives can be present in the photoimaging composition. Polymeric binders can be added to thicken the formulations or adhere them to substrates. The binders can also serve as a matrix for the color-forming composition. Light-transparent and film-forming polymers are preferred. Examples are ethyl cellulose, polyvinyl alcohol, polyvinyl chloride, polystyrene, polyvinyl acetate, poly(methyl, propyl or butyl methacrylate), cellulose acetate, cellulose butyrate, cellulose acetate butyrate, cellulose nitrate, chlorinated rubber, copolymers of the above vinyl monomers, etc. The binder can be present in an amount from about 0.5 part to 200 parts by weight per part of combined weight of the hexaphenylbiimidazole and leuco dye. Generally 5 to 20 parts by weight are used.


The binder composition can also contain inert infusible fillers such as titanium dioxide, organophilic colloidal silica, bentonite, powdered glass, micron-sized alumina and mica in minor, noninterfering amounts. Formulations containing micro-sized silicas, as, for example the "Syloid" silica gels, sold by W. R. Grace & Co., are particularly useful for providing a "tooth" for pencil or ink receptivity and eliminating blocking tendencies.

With some polymers, it is desirable to add a plasticizer, e.g., solid or liquid, to give flexibility to the film or coating. Suitable plasticizers are disclosed in U.S. Patent 3,658,543, column 10, lines 20 to 73. A preferred liquid plasticizer is Nonylphenoxypoly(ethyleneoxy)-ethanol. A preferred solid plasticizer is N-ethyl-p-toluenesulphonamide. The plasticizers can be used in concentration ranging from 1:20 to 5:3, preferably 1:5 to 1:2, based on the weight of polymeric binder used.

In preparing the formulation generally inert solvents are employed which are volatile at ordinary pressures. Examples include alcohols and ether alcohols such as methanol, ethanol, 1-propanol, 2-propanol, butanol, and ethylene glycol; esters such as methyl acetate and ethyl acetate; aromatics such as benzene, o-dichlorobenzene and toluene; ketones such as acetone, methyl ethyl ketone and 3-

pentanone; aliphatic halocarbons such as methylene chlorid, chloroform, 1,1,2-trichloroethane, 1,1,2,2-tetrachloroethane and 1,1,2-trichloroethylene; miscellaneous solvents such as dimethyl sulfoxide, pyridine, tetrahydrofuran, dioxane, dicyanocyclobutane and 1-methyl-2-oxo-hexamethyleneimine; and mixtures of these solvents in various proportions as may be required to attain solutions. It is often beneficial to leave a small residue of solvent in the dried composition so that the desired degree of imaging can be obtained upon subsequent irradiation.

Useful optional antiblocking agents present to prevent the coatings from adhering to one another include



and other known agents.

In the photopolymerizable embodiment of this invention, in addition to the hexaphenylbiimidazole compounds described above, at least one addition polymerizable ethylenically unsaturated compound having at least one polymerizable ethylenic group is present. Such compounds are capable of forming a high polymer by free-radical initiated, chain-propagating, addition polymerization. Preferably, the monomeric compound has at least two terminal ethylenically unsaturated groups, e.g., 2 to 4 groups. The monomeric compounds are nongaseous, i.e., at 20°C and atmospheric pressure, have a normal boiling point about 100°C and a plasticizing action on any thermoplastic polymeric binder that may be present.

Ethylenically unsaturated monomeric compounds useful in this invention include monomeric compounds or polymers wherein the ethylenic unsaturation is present as an extralinear substituent attached to the polymer backbone. Useful monomeric compounds are: alkylene or a polyalkylene glycol diacrylate prepared from an alkylene glycol of 2 to 15 carbons or a polyalkylene ether glycol of 1 to 10 ether linkages; unsaturated esters of alcohols, preferably polyols and particularly such esters of the aliphatic methylene carboxylic acids, e.g., ethylene glycol diacrylate, diethylene glycol diacrylate, glycerol diacrylate, glycerol triacrylate, ethylene glycol dimethacrylate, 1,3-propanediol dimethacrylate, 1,2,4-butanetriol trimethacrylate, 1,4-cyclohexanediol diacrylate, 1,4-benzenediol dimethacrylate, pentaerythritol tetramethacrylate, 1,3-propanediol diacrylate, 1,5-pentanediol dimethacrylate, pentaerythritol triacrylate; the bisacrylates and methacrylates of polyethylene glycols of molecular weight 200—500, etc.; unsaturated amides, particularly those of the alpha-methylene carboxylic acids, and especially those of alpha-omega-diamines and oxygen-interrupted omega-diamines, such as methylene bis-acrylamide, methylene bis-methacrylamide, ethylene bis-methacrylamide, 1,6-hexamethylene bis-acrylamide, diethylene triamine trimethacrylamide, bis(gamma-methacrylamidopropoxy) ethane, beta-methacrylamidoethyl methacrylate, N-(beta-hydroxyethyl)-beta-(methacrylamido) ethyl acrylate and N,N-bis(beta-methacryloxyethyl) acrylamide; vinyl esters such as divinyl succinate, divinyl adipate, divinyl phthalate, divinyl terephthalate; divinyl benzene-1,4-disulfonate, and divinyl butene-1,4-disulfonate, styrene and derivatives thereof and unsaturated aldehyde, such as sorbaldehyde (hexadienal).

Useful polymers having ethylenically unsaturated groups attached thereto are: the polymerizable, ethylenically unsaturated polymers of U.S. Patent 3,043,805 and U.S. Patent 2,929,710, e.g., polyvinyl acetate/acrylate, cellulose acetate/acrylate, cellulose, acetate/methacrylate, N-acryloyloxymethyl polyamide, etc.; polyoxyethylated trimethylol propane triacrylate, polytetramethylene glycol diacrylate, etc., disclosed in U.S. Patent 3,418,295.

Suitable thermal polymerization inhibitors that can be used in photopolymerizable compositions include p-methoxyphenol, hydroquinone, and alkyl- and aryl-substituted hydroquinones and quinones, tert-butyl catechol, pyrogallol, copper resinate, naphthylamines, beta-naphthol, cuprous chloride, 2,6-di-tert-butyl-p-cresol, phenothiazine, pyridine, nitrobenzene and dinitrobenzene. Other useful inhibitors, include p-toluquinone and chloranil, and thiazine dyes, e.g., Thionine Blue G (C. I. Basic Blue 25), and Toluidine Blue O (C. I. Basic Blue 17). In certain embodiments of the invention containing certain dye photoinitiators, however, no thermal inhibitor is required since these initiators have a dual function and in the dark serve as thermal inhibitors.

Free radical producing, electron donor agents (hydrogen donor) and active methylene compounds that can be present in the photopolymerizable photoimaging composition are described in U.S. Patent 3,479,185, column 2, line 50 to column 3, line 3. The electron donor agent has a reactive atom, usually hydrogen, which is removable and in the presence of the radical of the substituted 2,4,5-triphenylimidazolyl dimer yields a radical which reacts with the monomeric compound to initiate growth of polymer chains.

Examples of preferred electron or hydrogen donor compounds include compounds that form a stable composition with the hexaphenylbiimidazole compound in the dark. The agent can be an amine, e.g., a tertiary amine. The amine-substituted leuco dyes are useful, especially those having at least one dialkylamino group. Also, any leuco triphenylamine dye or various salts of the dye, e.g., the HCl salt of the leuco blue dye can be used. Illustrations of suitable dyes include tris-(4-N,N-diethylamino-o-tolyl)-methane trihydrochloride, bis(4-N,N-diethylamino-o-tolyl)triphenylmethane, bis(4-N,N-diethylamino-o-

tolyl) methylenedioxyphenylmethane, leuco neutral shade dye, i.e., bis(4-N,N-diethylamino-o-tolyl)-benzylthiophenylmethane, Leuco Malachite Green (C. I. Basic Green 4), leuco forms of Crystal Violet, Brilliant Green (C. I. Basic Green 1), Victorial Green 3B (C. I. Basic Green 4), Acid Green GG (C. I. Acid Green 3), Methyl Violet (C. I. Basic Violet 1), Rosaniline (C. I. Basic Violet 14), etc. The salt forms, e.g.,
 5 HCl salt, salts with Lewis acid, sulfuric acid salts, p-toluene sulfonic acid salts, etc., of the leuco dye is preferred for use.

Additional suitable, electron donor agents which can be used singly or in combination include aniline, N-methylaniline, N,N-diethylaniline, N,N-diethylcresidine, triethanolamine, ascorbic acid, 2-allylthiourea, sarcosin, N,N-diethylglycine, trihexylamine, diethylcyclohexylamine, N,N,N',N'-tetra-
 10 methylethylenediamine, diethylaminoethanol, ethylaminoethanol, N,N,N',N'-ethylenediaminetetraacetic acid, N-methylpyrrolidone, N,N,N',N'',N''-pentamethyldiethylenetriamine, N,N-diethylxylidene, N,N'-dimethyl-1,4-piperazine, N- β -hydroxyethylpiperidine, N-ethylmorpholine, and related amino compounds. While the tertiary amines and especially the aromatic tertiary amines having at least one CH₂ group adjacent to the nitrogen atoms are preferred, a combination of two radical generating agents
 15 such as a tertiary amine, e.g., N,N-dimethylaniline, and a secondary amine, e.g., N-phenylglycine, appear especially useful.

In a photoimaging composition containing the hexaphenylbiimidazole, monomeric compound and electron donor agent, the light-sensitivity, speed, or degree of polymerization is dependent on the concentration of the hexaphenylbiimidazole and electron donor agent. Useful compositions may be
 20 limited in part by the solubilities of the components. It was discovered that the speed increased up to a certain concentration of hexaphenylbiimidazole and electron donor agent, and an increase of the concentration past that level did not produce any increase in speed and in some instances the speed dropped. When a leuco dye was used as the electron donor agent, a mole ratio of leuco dye to the hexaphenylbiimidazole of 1.0 to 1.4 gave the best results as to photospeed and stability.

As indicated above, optionally, but preferably, a polymeric binder can be present in the photopolymerizable photoimaging system. Suitable binders include: the polymerized methylmethacrylate resins including copolymers thereof, polyvinyl acetals such as polyvinyl butyral and polyvinyl formal, vinylidene chloride copolymers (e.g., vinylidene chloride/acrylonitrile, vinylidene chloride/methacrylate and vinylidene chloride/vinylacetate copolymers), synthetic rubbers (e.g., butadiene/acrylonitrile
 30 copolymers and chloro-2-butadiene-1,3-polymers, cellulose esters (e.g., cellulose acetate, cellulose acetate succinate and cellulose acetate butyrate), polyvinyl esters (e.g., polyvinyl acetate/acrylate, polyvinyl acetate/methacrylate and polyvinyl acetate), polyvinyl chloride and copolymers (e.g., polyvinyl chloride/acetate), polyurethanes, polystyrene and the polymeric binders described in U.S. Patent 3,418,295. The monomeric compound and polymeric binder are present in the photoimaging
 35 composition in from 3 to 97 to 97 to 3 parts by weight, respectively. 0.001 to 2.0 parts by weight per 100 parts by weight of monomer and binder of a thermal addition polymerization inhibitor preferably is present.

Solvents, plasticizers, e.g., 10 to 50 percent by weight based on the weight of monomer, antiblocking agents, ultraviolet absorbers as described in the Examples, e.g., Example 18, can be
 40 present in the photopolymerizable photoimaging composition. In addition, oxygen scavengers, e.g., 2-allyl thiourea, dimethylsulfoxide, stannous chloride, N-phenylglycine, etc., can be present. The oxygen scavenger appears to eliminate or reduce the induction period usually found in a photopolymerization reaction, possibly by consumption of oxygen in the layer prior to exposure.

Another additive that can be present in the photopolymerizable composition is a chain transfer agent, in an amount of from 0.01 to 0.1 mol/mol electron donor agent such as a leuco dye, e.g., N-phenylglycine, 1,1-dimethyl-3,5-diketocyclohexane, or organic thiols, e.g., 2-mercaptobenzothiazole, 2-mercaptobenzoxazole, 2-mercaptobenzimidazole, pentaerythritol tetrakis (mercaptoacetate), 4-acetamidothiophenol, mercaptosuccinic acid, dodecanethiol, beta-mercaptoethanol, beta-mercaptoethanol, or other organic thiol.
 45

Still another additive is an energy-transfer dye of the type disclosed in U.S. Patent 3,479,185, column 5, lines 57 to 74. Generally such energy-transfer dyes are present in 0.5 to 3.0% by weight based on the weight of monomer or binder component, if present.

For imaging uses, the compositions of this invention may be coated upon or impregnated in substrates following known techniques. Substrates include materials commonly used in the graphic
 55 arts and in decorative applications such as paper ranging from tissue paper to heavy cardboard, films of plastics and polymeric materials such as regenerated cellulose, cellulose acetate, cellulose nitrate, polyethylene terephthalate, vinyl polymers and copolymers, polyethylene, polyvinyl-acetate, polymethyl methacrylate, polyvinylchloride; textile fabrics; glass, wood and metals. The composition, usually as a solution in a carrier solvent described above, may be sprayed, brushed, applied by a roller or an
 60 immersion coater, flowed over the surface, picked up by immersion or spread by other means, and the solvent evaporated.

Any convenient source providing radiation of wavelengths in the range of 200 nm to 420 nm can be used to activate the photoimaging composition for triphenylimidazolyl radical formation, image formation, and photopolymerization initiation. The radiation may be natural or artificial, monochromatic
 65

or polychromatic, incoherent or coherent, and should be sufficiently intense to activate a substantial proportion of the photoinitiator.

Conventional light sources include fluorescent lamps, mercury, metal additive and arc lamps. Coherent light sources are the pulsed nitrogen-, xenon, argon ion- and ionized neon-lasers whose emissions fall within or overlap the ultraviolet or visible absorption bands of the photoinitiator. Ultraviolet and near-visible radiation-emitting cathode ray tubes widely useful in printout systems for writing on photosensitive materials are also useful with the subject compositions.

Images may be formed by writing with a beam of the activating light or by exposing to such light a selected area behind a negative, stencil, or other relatively opaque pattern. The negative may be silver on cellulose acetate or polyester film or one in which its opacity results from aggregations of areas having different refractive indices. Image formation may also be effected in conventional diazo printing apparatus, graphic arts exposure or electronic flash equipment and by projection as described in U.S. Patent 3,661,461. The light exposure time may vary from a fraction of a second to several minutes, depending upon the intensity and spectral energy distribution of the light, its distance from the composition, the nature and amount of the composition available, and the intensity of color in the image desired.

Best Mode for Carrying Out the Invention

The best mode is illustrated in Example 1 wherein the hexaarylbiimidazole compound is 2,2',4,4'-tetrakis(o-chlorophenyl)-5,5'-bis(m,p-dimethoxyphenyl)-biimidazole.

Industrial Applicability

The hexaphenylbiimidazoles are useful as photoinitiators in various photoimaging formulations which can be used in the manufacture of dual response photoimaging products, where controlled sequential exposure with ultraviolet and visible light may yield negative or positive images, e.g., Dylux proofing papers, printout paper, e.g., for the Du Pont "aca" automatic clinical analyzer; garment pattern papers, overlay films, heatfix type papers and films; and in photopolymerizable layers and elements useful for printing purposes as well as a variety of copying, i.e., office copying, recording, decorative, and photoresist applications. The formulations containing the hexaarylbiimidazoles have improved absorption in the imaging areas of 345 to 400 nm and form imidazolyl radicals with increased radical life which permits their more effective utilization at lower concentration levels. The black formulation may be imaged with a variety of exposure sources, e.g., black light blue (B L B), black light, xenon, mercury vapor, etc. without use of a filter due to extended absorption. The stability of the formulations is improved. It is possible to fix the formulations faster because a lower amount of hexaphenylbiimidazole compound is present and must subsequently be destroyed during fixing. The imaging speed is also improved at equal concentration levels with current photoinitiators. Cost of the formulations is reduced because of the lower cost of ingredients for manufacture of the biimidazole as well as the fact that lower concentrations can be used.

Examples

The following examples illustrate the invention wherein the percentages are by weight.

Examples 1 to 10

Synthesis of Hexaphenylbiimidazoles

The asymmetrical hexaphenylbiimidazoles of this invention are prepared according to the following procedures.

A. Benzoin Condensation

To a one-liter flask equipped with a stirrer, reflux condenser and nitrogen inlet tube is charged:

	Ingredient	Amount (g)
	3,4-Dimethoxybenzaldehyde	200 (1.20 mols)
	2-Chlorobenzaldehyde	174 (1.24 mols)
	Methanol	225 ml
	Water	65 ml
	Potassium Cyanide	10

The system is purged with nitrogen, and the reaction mixture is refluxed for 45 minutes. The flask is cooled in an ice bath to induce crystallization which is followed by an additional 4.25 hours refluxing and cooling to room temperature with stirring. The precipitated benzoic is filtered off, is washed with a

0024629

175 ml methanol/25 ml water mixture, followed by a 1000 ml of water wash and is then recrystallized from ethanol. Table 1 summarizes the results of the benzoin preparation. Except for the indicated variations in the molar scale of the reactions, the procedure described above was followed with appropriate modification of the amounts of reactants.

TABLE 1

Benzoin $R-CO-CH(OH)R_1$

R aldehyde	R ₁ Aldehyde	Reaction Scale (Molar)	M.P. (°C)	Yield (%)
3,4-dimethoxy	2-chloro	1.2	116—118	69
3,4-dimethoxy	2-bromo	0.2	122—124	58
3,4-dimethoxy	2-methyl	1.0	118—9	23 ¹
4-ethoxy	2-chloro	1.2	123—5	74
3,4-dimethoxy	4-chloro	1.2	100—2	21 ²
3,4-dimethoxy	2-fluoro	0.9	124—6	52
3,4-methyl-eneoxy	2-chloro	1.2	115—6	63

1 Oil from reaction; crystals obtained from ether extraction.

2 Oil from reaction; crystals obtained from ethanol/petroleum ether.

B. Benzil Synthesis

To a 3-liter flask fitted with a stirrer, reflux condenser and thermometer, is added Mixture 1 which contains the following ingredients in the amounts indicated:

Mixture 1

Ingredient	Amount (g)
Cupric acetate	2.18
Water	121.0
Acetic acid	303.0
Ammonium nitrate	112.0

Mixture 1 is heated to about 95°C to obtain a solution. Mixture 2 is prepared from the following ingredients in the amounts indicated:

Mixture 2

Ingredient	Amount (g)
3,4-Dimethoxy-2'-chlorobenzoin	303.0
Acetic acid	909.0

Mixture 2 is heated to 70—80°C to maintain solution and is added portionwise to Mixture 1 in the flask as follows:

Portion 1: about 10% (~120 g) of Mixture 2 to start the reaction; nitrogen evolution is observed in 1 to 3 minutes.

Portion 2: About 40% (~450 g) of Mixture 2; the reaction temperature is maintained at 95 to 105°C.

Portion 3: Balance of Mixture 2 (~600 g) 1 to 2 hours after addition of Portion 2; the temperature of the mixture is held at 105°C for an additional hour.


5

Following an additional five-hour reflux period to complete the reaction, the mixture is allowed to cool overnight to room conditions. The mixture is chilled to 5 to 10°C with stirring and is filtered twice, first with a water (80 g)/acetone (320 g) solution chilled to 5 to 10°C, and then with 2000 ml of water. The filter cake is held for the preparation of the hexaphenylbiimidazoles. Table 2 summarizes the results of benzil preparation.

10

TABLE 2

15



20

25

30

<u>R₂</u>	<u>R₃</u>	<u>M.P. (°C)</u>
3,4-dimethoxy	2—Cl	
3,4-dimethoxy	2—Br	122—124
3,4-dimethoxy	2-methyl	124—126
4-ethoxy	2—Cl	90—91
3,4-dimethoxy	4—Cl	135—136
3,4-dimethoxy	2—F	96—98
3,4-methyleneoxy	2—Cl	91—92

35

C. Imidazole Synthesis

To a 500 ml flask equipped with a stirrer, reflux condenser and nitrogen inlet tube is charged:

40

45

50

<u>Ingredient</u>	<u>Amount (g)</u>
Benzil Compound	(See Table 3 below) (0.133 mol)
Benzaldehyde compound	(See Table 3 below) (0.146 mol)
Ammonium acetate	45
Glacial acetic acid	120 ml

55

60

65

The reaction mixture is swept with nitrogen and refluxed for 12 hours and allowed to cool to room temperature overnight. The reaction mixture is then poured into 2 liters of distilled water containing 7 g of potassium bisulfite to complex the unreacted aldehyde. A white solid precipitates which is filtered, washed with 2000 ml water, and dried. N.M.R. analysis shows that the acetate salt of the imidazole formed. No attempt is made to prepare the free base because in the final step of the synthesis the oxidative dimerization is carried out in strong base and the acetate salt is converted to the base at that stage.

0 024 629

TABLE 3


Compound No.	Benzil Compound	Amount (g)
1.	3,4-Dimethoxy-2'-chlorobenzil	40.6
2.	3,4-Dimethoxy-2'-fluorobenzil	38.3
3.	4-Ethoxy-2'-chlorobenzil	38.3
4.	3,4-Dimethoxy-2'-chlorobenzil	40.6
5.	3,4-Methylenedioxy-2'-chlorobenzil	33.8
6.	3,4-Dimethoxy-4'-chlorobenzil	40.6
7.	3,4-Dimethoxy-2'-chlorobenzil	40.6
8.	3,4-Dimethoxy-2'-chlorobenzil	40.6
9.	3,4-Dimethoxy-2'-methylbenzil	37.8
10.	3,4-Dimethoxy-2'-bromobenzil	46.4

TABLE 4

Compound No.	Benzaldehyde Compound	Amount (g)
1.	2-Chlorobenzaldehyde	20.6
2.	2-Chlorobenzaldehyde	20.6
3.	2-Chlorobenzaldehyde	20.6
4.	2-Bromobenzaldehyde	27.0
5.	2-Chlorobenzaldehyde	20.6
6.	2-Chlorobenzaldehyde	20.6
7.	2-Methylbenzaldehyde	17.5
8.	2,4-Dichlorobenzaldehyde	25.4
9.	2-Chlorobenzaldehyde	20.6
10.	2-Chlorobenzaldehyde	20.6

Table 5 summarizes the results of triphenylimiazole preparation.

TABLE 5



	A	A'	B	C	D	D'
1.	Cl	—	OCH ₃	OCH ₃	Cl	—
2.	Cl	—	OCH ₃	OCH ₃	F	—
3.	Cl	—	—	OEt	Cl	—
4.	Br	—	OCH ₃	OCH ₃	Cl	—
5.	Cl	—	O—CH ₂ —O*	—	Cl	—
6.	Cl	—	OCH ₃	OCH ₃	—	Cl
7.	CH ₃	—	OCH ₃	OCH ₃	Cl	—
8.	Cl	Cl	OCH ₃	OCH ₃	Cl	—
9.	Cl	—	OCH ₃	OCH ₃	CH ₃	—
10.	Cl	—	OCH ₃	OCH ₃	Br	—

*derived from piperonal

The dimers of the triphenylimidazolyl radicals derived from each of the specific triphenylimidazoles shown in Table 5 above are prepared by the following procedure. Into a 250 ml flask equipped with stirrer and condensor is placed one of the ten triphenylimidazoles in the amount indicated:

0 024 629

	Ingredient	Amount (g)
	Triphenylimidazol (0.0471 mol)	
5	1.	20.0
	2.	19.2
	3.	19.2
10	4.	22.1
	5.	19.2
15	6.	20.0
	7.	19.0
	8.	21.7
20	9.	19.0
	10.	22.1
25	Methylene chloride	125.0 ml
	K ₃ Fe(CN) ₆	20.7
	Water	65.0 ml
30	Sodium hydroxide (50%)	20.0

After refluxing for about 18 hours and cooling, 100 ml of water is added. The methylene chloride layer is separated and the aqueous phase is extracted with 50 ml methylene chloride. The combined methylene chloride layers are washed twice with 70 ml water and are dried over anhydrous sodium sulphate. The methylene chloride is evaporated carefully to determine the yield and methylene chloride is added to make a 15% solution.

TABLE 6

	Dimer No. and Rank ^(a)	Conversion (%)	Molar Extinction Coefficient*		Density (Trans). Speed		
			350 nm ^(b)	400 nm ^(c)	Dmax	Step	Dmin
40	1.	88	5763	1451	0.73	0.59	0.30
45	2.	58	4633	506	0.68	0.56	0.26
	3.	65	4672	253	0.65	0.45	0.22
50	4.	89	4941	588	0.57	0.41	0.19
	5.	54	5848	1089	0.60	0.39	0.17
55	6.	85	4364	844	0.81	0.48	0.2
	7.	96	5338	1128	0.46	0.41	0.19
	8.	79	4598	1150	—	0.45	0.24
60	9.	88	5338	502	0.60	0.45	0.29
	10.	70	4706	971	0.78	0.52	0.28

*Molar Extinction Coefficient is determined in methylene chloride at 10⁻⁵ to 10⁻³ mol/liter, the values being expressed in liters/mol cm.

(a) Visual comparison of sensitometric strips, lowest number is fastest. Dimers derived from triphenylimidazoles Table 5.

(b) Extinction coefficient for Control 2, Example 11 is 410 and Control 1, Example 11 is 2550.

(c) Extinction coefficient for Controls 1 and 2, Example 11 are <200.

5 The above ten triphenylbiimidazolyl dimers are used as new photoinitiators in photosensitive compositions containing the following ingredients in the amounts indicated:

	Ingredient	Amount (weight %)
10	Acetone (solvent)	72.000
	Isopropanol (solvent)	8.000
15	Dodecylbenzenesulfonic acid (proton acid)	0.727
	Tris(p-diethylamino-o-tolyl)methane (leuco cyan dye)	0.275
20	N-Ethyl-p-toluenesulfonamide (solid plasticizer)	2.890
25	o-Phenylphenol condensate with average of ~2.25 mols ethyleneoxide (plasticizer)	2.385
	Triphenylimidazolyl dimer (photoinitiator)* (one of compounds 1 to 10, Table 6)	0.434
30	Mixture of ~83% 1,6- and ~17% 1,8- pyrenequinones (oxidant)	0.004
	9,10-Phenanthrenequinone (oxidant)	0.139
35	Triethanolamine triacetate (hydrogen donor)	2.013
40	$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2\text{O}-\overset{\text{O}}{\parallel}{\text{C}}-(\text{CH}_2)_{16}\text{CH}_3$ (anti-blocking agent)	0.020
45	Silica gel of 9 μm average particle diameter surface area of 675 meters squared per gram, bulk density ~465 kg/m^3 (anti-blocking agent)	0.606
50	Cellulose acetate butyrate (~27% butyryl) content, ~1 hydroxyl/2 anhydroglucose units, and a viscosity of 56—131 poises by ASTM D—817—65—D (binder)	10.507
	Total	100.000

55 *added as a 15% solution by weight in methylene chloride (2.2 ml)

The photosensitive compositions are coated with a 0.004 inch (~ 100 nm) doctor blade on Schweitzer 32—HG paper and are dried at normal room conditions. The dry coatings are imaged by exposure through an image-bearing transparency for 30 seconds to 2.75 microwatts/cm² of black light blue radiation and are deactivated by exposure to room light to remove yellow background and render coatings insensitive to further ultraviolet irradiation. All the compositions provide good colored images with low background density.

65

0 024 629

Example 11

Three coating lacquers are prepared as follows:

	Ingr di nt	Amount (g)
5	Acetone	184.0
10	Cellulose acetate butyrate ~27% butyryl content hydroxyl/2 anhydroglucose units and viscosity is 7.5—15 poises by ASTM D—817—65—D	24.0
15	o-Phenylphenol condensed with average of ~2.25 mols ethylene oxide	16.0
20	[Tris-(2-methyl-4-diethylaminophenyl)- methane]	1.2
	p-Toluenesulfonic acid	1.4
	7-Diethylamino-4-methylcoumarin	0.4

25 To each of three 11.4 aliquots of the above lacquers is added 1.6×10^{-4} mol of one of the following hexaphenylbiimidazole compounds:

1. 2,2'-bis(o-chlorophenyl)-4,4',5,5'-tetrakis-(m-methoxyphenyl)-biimidazole (Control 1)
2. 2,2'-bis(o-chlorophenyl)-4,4',5,5'-tetraphenylbiimidazole (Control 2)
3. 2,2',4,4'-tetrakis(o-chlorophenyl)-5,5'-bis-(m,p-dimethoxyphenyl)-biimidazole.

30 Films are cast with a 040 coating bar on Schweitzer 32—HG paper and are dried at normal room conditions. Portions of the films are exposed as indicated in Table 7. The reflectance densities are measured with a MacBeth Quantalog reflectance densitometer.

35

40

45

50

55

60

65.

TABLE 7

Exposure Source	Tim (sec)	Reflectance Densities Coatings		
		1	2	3
1. None		0.08	0.04	0.09
2. Black light blue (365 nm peak)	60	1.46	1.53	1.65
3. Vivitar® 292 Photoflash 6000°K, no filter	0.001	1.52	1.52	1.55
4. Same as source 3 but use 0—51 filter ^(a)	0.001	1.08	1.03	1.25
5. Same as source 3 but use 3—75 filter ^(b)	0.001	0.99	0.99	1.10
6. Same as source 3 but use 3—74 filter ^(c)	0.001	0.66	0.44	0.69
7. Same as source 3 but use 3—72 filter ^(d)	0.001	0.24	0.18	0.45

(a) less than 0.5% transmission at less than 334 nm; greater than 65% transmission at greater than 405 nm

(b) less than 0.5% transmission at less than 373 nm; greater than 65% transmission at greater than 427 nm

(c) less than 0.5% transmission at less than 403 nm; greater than 65% transmission at greater than 436 nm

(d) less than 0.5% transmission at less than 444 nm; greater than 65% transmission at greater than 46 nm

This example illustrates that the hexaphenylbiimidazole compound of the invention present in coating 3 has greater absorption of actinic radiation at longer wavelengths as compared to the two control hexaphenylbiimidazole compounds present in coatings 1 and 2.

Examples 12 to 18 which follow illustrate various uses for the preferred hexaphenylbiimidazole compound, 2,2',4,4'-tetrakis(o-chlorophenyl)-5,5'-bis-(m,p-dimethoxyphenyl)-biimidazole.

O 024 629**Example 12**

This example illustrates a magenta color-forming system.

A coating solution is prepared by mixing the following ingredients in the amounts indicated:

5	<u>Ingredient</u>	<u>Amount (g)</u>
	Methylene chloride	295.0
	Isopropanol	21.0
10	Cellulose acetate butyrate described in Example 11	42.2
	Triethanolamine triacetate	0.01
15	1-Phenylpyrazolidine-3-one	0.106
	p-Toluenesulfonic acid	0.347
20	N-Ethyl-p-toluenesulfonamide	3.93
	Nonylphenoxypoly(etheneoxy)- ethanol, nonionic surfactant and plasticizer	3.93
25	7-Diethylamino-4-methylcoumarin	1.0
	hexaphenylblimidazole No. 3, Example 11	4.64

30 The solution is coated on 0.003 inch (0.076 mm) thick polyethylene terephthalate film with a 025
coating bar and is allowed to dry. A 10-second exposure to ultraviolet radiation from BLB lamps gives a
magenta image reflectance density of 0.64 when read over a white paper surface. A 20-second
35 exposure to visible light with SDZ fluorescent lamps, gives an optical density of 1.06. The coating is
deactivated by passing through a solution containing 235 g water, 115 g isopropanol, 3.5 g sodium
sulfite, 3.5 g acetic acid and 7.0 g 1-phenylpyrazolidine-3-one.

40

45

50

55

60

65

0 024 629

Example 13

This example illustrates a negative-working garment pattern paper.

A coating solution is prepared by mixing the following ingredients in the amounts indicated:

	Ingredient	Amount (g)
5	Methylene chloride	385.0
	Isopropanol	70.0
10	Cellulose acetate butyrate as in Example 11 except that the viscosity is 56—131 poises by ASTM D—817—65—D	38.0
15	Nonylphenoxypoly(etheneoxy)ethanol	28.0
	p-Toluenesulfonic acid	2.74
20	Silica gel of 9.0 μm average particle diameter, 675 m^2/gm surface area, bulk density $\sim 465 \text{ Kg/m}^3$	2.90
25	Mixture of $\sim 83\%$ 1,6- and $\sim 17\%$ 1,8- pyrenequinones	0.047
	Phenanthrenequinone	0.141
30	$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2\text{—O—C(=O)—(CH}_2\text{)}_{18}\text{CH}_3$	0.30
	7-Diethylamino-4-methylcoumarin	0.46
35	3,4-Dimethoxyphenyl-bis(4-diethylamine-2- methylphenyl) methane	0.38
	Rhodamine 5 GLD (C. I. 45160)	0.18
40	Hexaphenylbiimidazole No. 3, Example 11	0.57

The solution is coated on Schweitzer Sub 14 paper with a 010 coating bar to give a coating weight of $\sim 4.0 \text{ mg/dm}^2$. After exposure to an ultraviolet radiation source for 60 seconds, an optical density of 0.7 is obtained.

0 024 629

Example 14

This example illustrates the preparation of proofpaper, A yields cyan and B yields black images. A coating lacquer is prepared by mixing the following ingredients in the amounts indicated:

5

Coating A

	Ingredient	Amount (g)
10	Methylene chloride	37.1
	Isopropanol	4.1
	Cellulose acetate butyrate described in Example 13	5.2
15	Pyrenequinone as described in Example 13	0.0031
	Phenanthrenequinone	0.050
20	$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2\text{—O—}\overset{\text{O}}{\parallel}\text{C}(\text{CH}_2)_{16}\text{CH}_3$	0.044
	7-Diethylamino-4-methylcoumarin	0.078
25	Dodecylbenzenesulfonic acid	0.435
	Triethanolamine triacetate	0.96
30	o-Phenylphenol condensed with average of ~2.25 mols ethylene oxide	1.0
	Silica gel described in Example 13	0.35
35	Hexaphenylbiimidazole No. 3, Example 11	0.152

The solution is coated on Schweitzer 32—HG paper with an 020 bar, and the dried coating is exposed for 60 seconds to ultraviolet radiation (BLB lamps) through a lithographic negative. An image density of 1.0 is read on a MacBeth Quantalog® Reflectance densitometer. The coating can also be exposed in a positive manner, with the initial light source a bank of SDZ fluorescent lamps, through a lithographic negative, followed by a flooding exposure with BLB lamps. An image with density of 1.0, and background of 0.1 is attained.

A similar coating solution as described above, but containing 0.18 g of the hexaphenylbiimidazole instead of 0.152 g, results in increased contrast; 60 seconds exposure to ultraviolet radiation gives an optical density of 1.3, with background of 0.15, after 1 hour ambient light exposure.

The concentration of the hexaphenylbiimidazole is reduced further to 0.12 g in the above coating lacquer. A reduced optical density of 0.7 with background of 0.11 is obtained, after a 60-second exposure to ultraviolet radiation and a 1 hour ambient light exposure.

A coating lacquer in which 2,2'-bis-(o-chlorophenyl)-4,4',5,5'-tetrakis-(m-methoxyphenyl)-biimidazole is employed instead of the hexaphenylbiimidazole No. 3 as described above, requires 0.36 g to achieve an optical density of 1.05, with background of 0.1 and 0.61 g for an image density of 1.1. At the higher concentration, it is not possible to obtain a low background in a positive exposure mode, as a color buildup of 0.41 is observed. A lower background is observed, however, when samples are exposed in ambient light for an hour.

A coating lacquer is prepared by mixing the following ingredients in the amounts indicated:

60

65

0 024 629

Coating B

	Ingredient	Amount (g)
5	Methylene chloride	36.0
	Isopropanol	4.0
	Cellulose acetate butyrate described in Example 13	4.53
10	Phenanthrenequinone	0.045
	$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2\text{—O—}\overset{\text{O}}{\parallel}\text{C}(\text{CH}_2)_{16}\text{CH}_3$	0.038
15	3-Methoxy-4-octamidophenyl-bis(4-diethylamino-2-methylphenyl) methane	0.088
	Trans-3-hydroxy-2-(p-diethylaminobenzyl)-indanone	0.038
20	N-ethyl-p-toluenesulfonamide	0.98
	Dodecylbenzenesulfonic acid	0.493
25	Triethanolamine triacetate	1.66
	o-Phenylphenol condensed with average of ~2.25 mols ethylene oxide	1.19
30	Silica gel described in Example 13	0.30
	Hexaphenylbiimidazole No. 3, Example 11	0.30

35 The coating lacquer is coated on Schweitzer 32—HG paper with a 032 wire-wound rod, and dried with hot air. Exposure to BLB fluorescent lamps in a contact printer, at an irradiance of 6 mw/cm² through a silver negative generates black images with a density of 1.22. Substantially no color develops when the coating is exposed to 80 foot candles (~860 meter candles) of cool white fluorescent light for 1 hour, but a whitening of the yellow areas is noticed. The OD_{max} is 2.1: the OD_{min} is 0.15.

40

45

50

55

60

65

0 024 629

Example 15

This example illustrates a fast photofix composition.

A coating solution is prepared by mixing the following ingredients in the amounts indicated:

Ingredient	Amount (g)
Methylene chloride	107.0
Isopropanol	6.8
Cellulose acetate butyrate described in Example 13	11.3
Pyrenequinone as described in Example 13	0.0113
Phenanthrenequinone	0.225
$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2\text{O}-\overset{\text{O}}{\parallel}\text{C}(\text{CH}_2)_{16}\text{CH}_3$	0.101
7-Diethylamino-4-methylcoumarin	0.262
N-Ethyl-p-toluenesulfonamide	2.63
Dodecylbenzenesulfonic acid	3.375
Triethanolamine triacetate	4.123
o-Phenylphenol condensed with average of ~2.25 mols ethylene oxide	3.0
Silica gel described in Example 14	0.79
Hexaphenylbiimidazole No. 3, Example 11	0.64

The solution is applied onto Schweitzer 32—HG paper with a 010 coating bar, at a dry coating weight of 82 mg/dm². Exposure of the dried coating to ultraviolet radiation from a bank of BLB lamps, with an irradiance of 9 mw/cm² for 20 seconds produces an image density of 0.9 (reflectance). A positive image results when the coating is exposed through a lithographic negative for 10 seconds in a bank of SDZ fluorescent lamps, followed by a 5-second exposure to the BLB lamps. An image density of 0.8, with a background of 0.1 is observed.

A slightly lower image density results when 0.51 g of the hexaphenylbiimidazole is used instead of 0.64 g; the image density for coatings of about 80 mg/dm² is 0.7.

When 2,2'-bis(o-chlorophenyl)-4,4',5,5'-tetrakis-(m-methoxyphenyl)-biimidazole (control)* is used as photoinitiator, 1.28 g is required to achieve a similar level of performance as is achieved with the lower levels of the hexaphenylbiimidazole described above.

*On a molecular weight basis the hexaphenylbiimidazole of this example is 2.2 times better than the control hexaphenylbiimidazole.

0 024 629

Example 16

This example illustrates the preparation of a heat-fix formulation.
The following ingredients are mixed together in the amounts indicated:

5	Ingredient	Amount (g)
	Acetone	250.0
	Cellulose acetate butyrate described in Example 11	60.0
10	3,4-Dimethoxyphenyl-bis(4-diethylamino-2-methylphenyl)methane	2.48
	p-Toluenesulfonic acid	2.06
15	Di-t-butyl hydroquinone adduct with dihydropyran, mol wt is 274	2.88
	p-Cresol-ethylene oxide adduct, mol wt is ~170	18.0
20	Hexaphenylbiimidazole No. 3, Example 11	0.40

The formulation is coated with a 020 bar onto Schweitzer Sub 14 paper and dried with air. It is
25 imaged for 20 seconds by exposure through a negative with BLB ultraviolet lamps to give an image density of 1.09. The coated paper is brought into contact with an aluminum block heated to 300°F (149°C) for 15 seconds. Subsequent exposure to cool white fluorescent lamps [680 ft. candl s (~7320 meter candles) intensity] for 2.75 hours produces no further color, indicating that the photoinitiator is deactivated; background density is 0.05.

30

Example 17

This example illustrates a photopolymerizable composition containing a hexaphenylbiimidazole of the invention as a photoinitiator.

A prepolymer is prepared as follows: to 300 g of an aliphatic diisocyanate polymer, specific
35 gravity 1.07, Hylene® W, E. I. du Pont de Nemours and Company, Wilmington, DE stirred under nitrogen, is added 149 g of 2-hydroxyethylmethacrylate and 0.001 g of phenothiazine. Their reaction mixture is heated to 55°C, followed by two hours at 60°C.

The prepolymer is present in the following mixture:

40	Ingredient	Amount (g)
	Prepolymer (binder)	10.0
	Hexaphenylbiimidazole No. 3, Example 11	0.05
45	Michler's ketone (initiator)	0.02
	N-Phenylglycine (hydrogen donor)	0.04
50	Methylene chloride (solvent)	5.00

The mixture is stirred in the dark, and then is cast on a 0.003 inch (0.076 mm) thick polyethylene terephthalate film. After air-drying the coating is covered with a 0.001 inch (0.025 mm) thick
55 polyethylene terephthalate film, and the element formed is exposed to BLB ultraviolet lamps for 60 seconds. A tack-free photopolymer is observed.

A similar coating is made on a glossy paper with a 040 coating bar. It is overlaid with thin polyethylene terephthalate film and is exposed to give a tack-free coating after 60 seconds.

60

65

0 024 629

Example 18

A solution is prepared as follows:

	Ingredient	Amount (g)
5	1. Trimethylolpropanetrimethacrylate (monomer)	16.796
10	2. Monolauryl ether of tetra(oxyethylene) glycol (plasticizer)	5.599
	3. Methylene chloride (solvent)	441.600
15	4. (a) Copolymer of methylmethacrylate and ethylacrylate, mol wt 500,000 determined by gel permeation chromatography, Brookfield viscosity 10% in toluene, 25°C, 60 rpm, #1 spindle is 15 to 45 cps (binder)	25.529
20	(b) 2,2'-Dihydroxy-4-methoxy-benzophenone (UV absorber)	0.045
25	(c) 2-Mercaptobenzothiazole (chain transfer agent)	0.448
30	5. (a) 2-(Stilbyl-4'')-(naphtho-1',4,5)-1,2,3-triazole-2'-sulfonic acid phenyl ester (UV absorber)	0.112
	(b) 7-(4'-Chloro-6'-diethylamino-1',3',5'-triazine-4'-yl)amino-3-phenyl coumarin (UV absorber)	0.546

35 To a 10 g (1.0 g solids) aliquot of the above solution is added 0.183 g of one of the hexaphenylbiimidazole compounds of Example 11, i.e., 1, 2 or 3. The solutions are coated using a 0.075 mm knife onto sub-coated polyethylene terephthalate film, 0.075 mm in thickness, are air dried for about 10 minutes, and are laminated with a polyethylene terephthalate cover film, 0.025 mm in thickness. The photopolymer films having a coating weight of about 46 mg/dm² are each exposed for 2 seconds using the following sources:

40 (1) 2000 watt pulsed Xenon manufactured by nuArc Company, Chicago, Illinois [17 inches (43.18 cm) from vacuum frame].

(2) A bank of 10 black light blue fluorescent lamps manufactured by GTE Sylvania 18T8/BLB/40/180° maintained 2 inches (5.08 cm) from pressure held frame.

45 After exposure through a $\sqrt[3]{2}$ step wedge image the cover film is removed and colored toner is applied to each. The following results are obtained:

	Hexaphenylbiimidazole	Exposure Source	Photospeed*
50	1	1	5—12
	2	1	5—12
55	3	1	7—15
	1	2	5—11
60	2	2	5—11
	3	2	6—14

65 * $\sqrt[3]{2}$ (step wedge) step totally polymerized to step totally unpolymerized.

0024 629

The samples (3) using a hexaphenylbiimidazole compound of the invention are on the average about 1.8 and 1.67 faster than the controls (1 and 2) using exposure source 1 and 2, respectively.

Example 19

5 This example illustrates a high speed imaging system.

A coating solution is prepared by mixing the following ingredients in the amounts indicated:

	Ingredient	Amount (g)
10	Acetone	65.0
	Di-i-propylamine	1.0
15	p-Formylphenoxyacetic acid	0.8
	o-Formylphenoxyacetic acid	0.8
	Nonylphenoxypoly(etheneoxy)ethanol	1.0
20	Tricresyl phosphate	1.0
	Leuco Crystal Violet (C. I. 42555)	0.4
25	Benzophenone	0.6
	Ethylenediamine tetracetic acid	1.0
	Cellulose acetate butyrate described in Example 13	6.0
30	1-Phenylpyrazolidine-3-one	0.048
	Hexaphenylbiimidazole No. 3, Example 11	0.32

35 The solution is coated on Schweitzer 32—HG paper with a 0015 coating bar, and is exposed with BLB ultraviolet lamps for 10 seconds to give a reflectance optical density of 1.25. A 60-second exposure gives an optical density of 1.47. A 30-second exposure to visible light (SDZ lamps) gives an optical density of 1.36.

40

45

50

55

60

65

Examples 20 to 22

	Ingredient	Ex. 20	Amount (g) Ex. 21	Ex. 22
5	Methylene chloride	432.0	530.0	514.0
	Isopropanol	48.0	50.0	56.0
10	Dodecylbenzenesulfonic acid	4.31	—	—
	Tris(p-diethylamino-o-tolyl)methane	1.65	—	2.14
15	N-Ethyl-p-toluenesulfonamide	17.1	22.1	—
	o-Phenylphenol condensate with average of ~ 2.25 mols ethyleneoxide- (plasticizer)	14.1	18.3	32.2
20	Mixture of ~83% 1,6— and 17% 1,8-pyrenequinones	0.0234	—	—
	9,10-Phenanthrenequinone	0.826	0.273	—
25	Triethanolamine triacetate	11.95	15.5	—
	Silica gel of 9 μ average particle diameter surface area of 675 meters squared per gram, bulk density ~465 kg/m³	3.60	6.3	—
30	Cellulose acetate butyrate as described in Example 13	62.4	80.0	—
35	$\text{CF}_3(\text{CF}_2\text{CF}_2)_{17}\text{CH}_2\text{CH}_2-\text{O}-\overset{\text{O}}{\parallel}{\text{C}}$ <div style="margin-left: 150px;"> \mid $\text{H}_3\text{C}(\text{H}_2\text{C})_{16}$ </div>	0.12	—	—
40	p-Toluenesulfonic acid	—	3.23	2.24
	3-Methoxy-4-octamido-phenylbis(4- diethyl-amino-2-methylphenyl) methane	—	2.01	—
45	Trans-3-hydroxy-2-(p-diethylamino- benzyl)indanone	—	0.90	—
50	Cellulose acetate butyrate described in Example 11	—	—	92.0

60 BLB fluorescent lamps (BLB max) through a step tablet for 90 seconds with an irradiance of about 8 mw/cm², followed by a 90-second photodeactivation exposure using GTE Sylvania lamps which peak at 440—450 nm. Positive images (Pos. Im.) are prepared by initially exposing through a litho negative image for 90 seconds with the GTE Sylvania lamps followed by a 10-second exposure to the BLB lamps
65 after removing the negative.

0024 629

Example 22

(a) BLB fluorescent lamps through a step tablet for 90 sconds with an irradiance of about 8 mw/cm²;

(b) SDZ fluor sc nt lamps, directly for 60 seconds with an irradiance of about 3 mw/cm²;

(c) as in (b) but an interposed weatherable polyethylene terephthalate film is placed between the exposure source and the photosensitive coating.

The density readings are measured with a MacBeth Quantalog® densitometer for a visual density reading (reflectance mode).

For the film coatings a wide Morest® card as used for pigment drawdown is employed under the coated films. The steps column in Table 8 refers to the maximum number of steps totally polymerized.

TABLE 8

Blue (Ex. 20)

	Dimer (See Tables 5 & 6)	Mols X10 ³	Ctg. Wt. (mg/ dm ²)	BLB Max Reflect	Steps	Pos. Im. D _{max} /D _{min} Reflect
15	1	0.119	157	1.32	21	1.53/0.12
20	2	0.120	156	1.21	22	
25	4	0.118	145	1.35	21	1.46/0.18
	5	0.120	184	1.32	21	
	6	0.118	167	1.35	22	
30	7	0.120	185	1.20	20	1.25/0.12
	8	0.120	151	1.41	23	1.28/0.13
35	9	0.119	169	1.24	22	
	10	0.100	146	1.21	20	1.24/0.1
40	Control 1 (Example 11)	0.118	164	0.88	19	
45	Control 2 (Example 11)	0.118	210	0.99	15	0.97/0.14

0024 629

TABLE 8 (continued)

Dimer (See Tables 5 & 6)	Mols $\times 10^3$	Ctg. Wt. (mg/ dm^2)	Black (Ex. 21)		Pos. Im. $D_{\text{max}}/D_{\text{min}}$ Reflect
			BLB Max Reflect	Steps	
1	0.119	133	1.29	21	1.32/0.12
2	0.120	131	1.08	21	1.17/0.11
4	0.118	141	1.34	25	1.30/0.16
5	0.120	133	1.32	22	1.29/0.14
6	0.118	149	1.12	22	
7	0.120	136	1.21	20	1.23/0.11
8	0.120	185	1.08	20	
9	0.119	138	1.03	20	
10	0.100	165	0.77	20	
Control 1 (Example 11)	0.118	131	1.21	17	1.20/0.17
Control 2 (Example 11)	0.118	140	0.53	11	0.51/0.12

0 024 629

TABLE 8 (continued)

Blu — No Fix (Ex. 22)					
Dimer (See Tables 5 & 6)	Mols X10 ³	BLB (a) Max Reflect	Steps	SDZ (b) Reflect	SDZ (c) Reflect
1	0.119	1.60	24	1.52	0.73
2	0.120	1.58	24	1.59	0.76
3	0.120	1.72	24	1.30	0.53
4	0.118	1.50	25	1.46	0.72
5	0.120	1.70	25	1.60	0.71
6	0.118	1.49	23	1.35	0.58
7	0.120	1.48	24	1.44	0.57
8	0.120	1.51	23	1.31	0.77
9	0.119	1.50	23	1.35	0.47
10	0.100	1.44	25	1.40	0.66
Control 1 (Example 11)	0.118	1.72	24	1.13	0.33
Control 2 (Example 11)	0.118	1.65	20	1.19	0.41

0 024 629

Example 23

The following stock solution is prepared:

	Ingredient	Amount (g)
5	2-(Stilbyl-4'')-(naphtho-1',4,5)-1,2,3-triazole-2'-sulfonic acid Phenyl ester (UV absorber)	0.78
10	7-(4'-Chloro-6'-diethylamino-1',3',5'-triazine-4'-yl)amino-3-phenyl coumarin (UV absorber)	3.88
15	Trimethylolpropanetrimethacrylate	139.50
	Polyoxyethylated trimethylol propane Triacrylate, mol wt 1000—1200	31.00
20	Monolauryl ether of tetra(oxyethylene)glycol (plasticizer)	31.00
25	Polymethylmethacrylate, Very high mol wt, Inherent Viscosity 1.37 determined in 0.25 g of CHCl ₃ , 25°C using a No. 50 Cannon-Fenske Viscometer	127.10
	Polyvinyl acetate ~86 monomer units chain length	49.60
30	2,2'-Dihydroxy-4-methoxy-benzophenone	0.31
	Hydroquinone	0.20
35	2-Mercaptobenzoxazole	2.79
	Methylene chloride	3476.00

To 38.6 g aliquots of this solution are added 9.4×10^{-5} mol of each of the photoinitiators listed in Table 6 (Controls as solids, Dimer 1 as 31% solution in methyl ethyl ketone, the rest as 15% solutions in methylene chloride). The solutions are stirred and are coated on polyethylene terephthalate supports using a 0.003 inch (0.076 mm) knife to yield a coating 0.0003 inch (0.0076 mm) in thickness. After air drying for about 10 minutes, a polypropylene cover sheet 0.00075 inch (0.019 mm) in thickness is applied using a squeegee. The coated films are exposed simultaneously through a $3\sqrt{2}$ step tablet to each of two radiation sources:

(1) 2000-watt pulsed xenon lamp in a nuArc® flip-top exposure frame, 20 seconds, 17 inches (43.18 cm) from the films in the pressure frame.

(2) Series of SDZ fluorescent lamps with an output of 450 ft.-candles (4840 meter-candles), 60 seconds, 2 inches (5.08 cm) from films in the pressure frame.

After exposure the cover sheets are removed and a colored toner is applied by dusting each exposed film. The following results are obtained, Table 9 illustrates radiation source (1) and Table 10 radiation source (2).

0 024 629

TABLE 9

	Dimer (See Tables 5 and 6)	Photospeed*	Photospeed**
5	1	7 to 10	1.63
	2	7 to 12	3.0
	3	5 to 9	1.13
10	4	7 to 10	1.63
	5	7 to 11	1.79
15	6	7 to 11	1.79
	7	7 to 9	1.50
	8	8 to 11	2.05
20	9	6 to 10	1.42
	10	6 to 9	1.29
25	Control 1, Example 11	5 to 11	
	Control 2, Example 11	4 to 9	1.00

*Step totally polymerized to step totally unpolymerized

30 **Speed factor relative to Control 2 which is 1.0; speed factor equals $\left[\left[\text{antilog} \left[(\text{step no. experimental} - \text{step no. control 2}) \times \log \left(\sqrt[3]{2} \right) \right] + \text{antilog} \left[(\text{step no. experimental} - \text{step no. Control 2}) \right] \right] \times \log \sqrt[3]{2} \right] \text{ divided by } 2$.

TABLE 10

	Dimer (See Tables 5 and 6)	Photospeed*	Photospeed**
35	1	12 to 14	1.13
40	2	13 to 15	1.42
	3	11 to 14	1.00
45	4	13 to 15	1.42
	5	12 to 15	1.26
	6	14 to 16	1.79
50	7	13 to 15	1.42
	8	14 to 16	1.79
55	9	13 to 15	1.42
	10	12 to 15	1.26
	Control 1, Example 11	11 to 14	
60	Control 2, Example 11	11 to 14	1.00

*Step totally polymerized to step totally unpolymerized

65 **Speed factor relative to Control 2 which is 1.0. Speed factor is determined by formula beneath Table 9.

0 024 629

Example 24

The following stock solution is prepared:

	Ingredient	Amount (g)
5	Michler's ketone	5.0
	Trimethylolpropane triacrylate	145.0
10	Triethyleneglycol diacetate	20.0
	Tricresyl phosphate	20.0
	Diethylphthalate	20.0
15	Peroxide-initiated polymethyl- methacrylate, high mol wt, inherent viscosity 1.37 determined in 0.25 g of CHCl ₃ , 25°C using a	
20	No. 50 Cannon-Fenske Viscometer	20.0
	Peroxide-initiated polymethyl- methacrylate, low mol wt, inherent viscosity 0.21 determined in 0.25 g of CHCl ₃ , 25°C using a	
25	No. 50 Cannon-Fenske Viscometer	145.00
	Victoria Pure Blue BO (CI 42595)	0.15
30	Benzotriazole	1.0
	Tris-(p-diethylamino-o-tolyl)methane	1.5
	Tris-(p-dimethylaminophenyl)-methane	0.5
35	Methylene chloride	2709.0

To 31.9 aliquots of this solution are added 3.03×10^{-4} mol of each of the photoinitiators listed in Table 6 (Controls as solids, Dimer 1 as 31% solution in methyl ethyl ketone, the rest as 15% solutions in methylene chloride). The solutions are stirred and are coated on polyethylene terephthalate films using a 0.010 inch (0.25 mm) knife to yield a coating 0.0015 inch (0.038 mm) in thickness. After air drying for 30 minutes, the films are laminated onto precleaned copper circuit boards at 40 psi (2.81 kg/sq cm) pressure and 220°F (105°C). The coated films are exposed for 30 units (about 90 seconds) through a 21 step $\sqrt{2}$ step tablet on a Berkey-Ascor unit (to a 2kw Addalux® mercury photopolymer type lamp). After the exposure, the polyethylene terephthalate films are removed and the unexposed areas are washed out during a one-minute development cycle in a Riston® processor using chloroethene. The following results are obtained:

50

55

60

65

TABLE 11

	Dimer (See Tables 5 and 6)	Photospeed*	Photospeed**
5	1	6 to 8	1.71
	2	6 to 8	1.71
10	3	6 to 7	1.41
	4	7 to 8	2.0
	5	6 to 8	1.71
15	6	5 to 6	1.0
	7	5 to 6.5	1.09
20	8	7 to 8	2.0
	9	6 to 7	1.41
	10	6 to 8	1.71
25	Control 1, Example 11	3 to 5	
	Control 2, Example 11	5 to 6	1.00

30 *Step totally polymerized to step totally unpolymerized.

**Speed factor relative to Control 2 which is 1.0. Speed factor is determined by formula beneath Table 9 except that $\log(\sqrt[3]{2})$ is replaced by $\log(\sqrt{2})$

35 It is known that imidazolyl radicals exhibit unique signals when examined in an electron spin resonance (esr) spectrometer; diminution of the signals indicates disappearance of the radical to give the starting dimer. It is further known that many biimidazole compounds on photolysis give rise to colored free radicals. In the absence of exciting radiation, these radicals recombine to give the starting dimer. This dimerization process may be speeded up by heat or increased plasticization of the medium. Techniques for measuring absorption spectra of the radicals or colorimetric measurements of films or

40 treated papers may thus be employed to make comparisons in the lifetime of imidazolyl radicals. The following Examples illustrate the increased radical lifetime of radicals formed from imidazolyl dimers of this invention.

Example 25

Electron Spin Resonance (esr) Measurements

45 (A) *Solutions* of 0.01 molarity in methylene chloride are made with Control 1 (Example 11) and hexaphenylbiimidazole No. 3, Example 11. These are inserted in 30 mm (ID) Pyrex® tubes inside the cavity of a Bruker® BR420 esr spectrometer, and are exposed to several flashes with an electronic flashgun (Exposure Source 3 of Table 7). The signal generated by the radical is recorded over a period of

50 time, and disappears completely after 200 seconds for the control. Signal strength of one-third the original is detected after more than 2000 seconds for hexaphenylbiimidazole No. 3, Example 11, a lifetime of over 10 times greater in solution for the radicals derived from the hexaphenylbiimidazole of this invention.

55 (B) *Films* are prepared by coating a lacquer containing 0.96 g cellulose acetate butyrate described in the photosensitive compositions of Examples 1 to 10, 0.15 g hexaphenylbiimidazole, and 8.0 g methylene chloride onto a polyethylene terephthalate film using a 032 coating bar. The film weight is approximately 0.056 g/dm². A film made with hexaphenylbiimidazole No. 3, Example 11, is inserted in a 4.0 mm (ID) Pyrex® tube, and is exposed for several minutes with ultraviolet light. The sample is

60 placed in the cavity of the above-described esr instrument, and the signal is recorded. After 66 hours the sample is scanned again. It retains 40% of the original signal strength. A similarly exposed film made with Control 1 (Example 11) shows a signal initially but shows no signal after 16 hours, indicating appreciably longer radical lifetime in films prepared containing the hexaphenylbiimidazole of this invention.

65 The solution (A) containing hexaphenylbiimidazole No. 3, Example 11, shows a single esr absorption 7 gauss wide with G-factor of 2.0028. This signal is also observed in irradiated films (B)

except that a slightly broader line width of 8 gauss is found.

Example 26

(A) Stability of Radicals By Optical Measurements

Films are prepared as described in Example 25 (B) except that the below listed hexaphenylbiimidazole compounds are used. The films are scanned in a Cary Model 17 spectrophotometer from 700 nm to 300 nm. Samples are then irradiated with ultraviolet light from BLB lamps for 110 seconds. Exposed samples are then returned to the spectrophotometer for additional scanning over the same wavelength range. The scanning is repeated after 22 hours. Approximately the same length of time is employed in handling each sample. Scanning from 700 to 300 nm takes about 4 minutes.

A wavelength is selected at which there is a maximum difference between the exposed and unexposed film sample. The 22-hour old sample shows a decrease in optical density at that wavelength. The decrease in radical concentration is determined according to the formula:

$$\text{Loss in radical OD}_{\text{IRR}} - \text{OD}_{22}$$

$$\text{concentration} = \text{OD}_{\text{IRR}} - \text{OD}_{\text{UN}}$$

$$(R\%)$$

where OD_{IRR} is the optical density of the film after irradiation, OD_{22} is the optical density of the film after 22 hours, and OD_{UN} is the optical density of the unirradiated film.

Sample	Wavelength (nm)	Formula	Loss (%)
Control 1, Example 11	380	$\frac{0.29 - 0.23}{0.29 - 0.23}$	100
Control 2 Example 11	360	$\frac{0.38 - 0.23}{0.38 - 0.18}$	75
Compound 10, Tables 5 and 6	460	$\frac{0.215 - 0.12}{0.215 - 0.065}$	63
Compound 3, Tables 5 and 6	400	$\frac{0.75 - 0.44}{0.75 - 0.21}$	57
Compound 1, Tables 5 and 6	400	$\frac{0.90 - 0.55}{0.90 - 0.23}$	52

These data show that the compounds of the invention have longer radical life versus the controls. The differences between the controls and hexaphenylimidazole compounds of this invention indicate that electronic effects, arising from substituents, as well as steric factors which may be present, as shown by 4-phenyl ortho-substituted compounds of this invention influence radical life.

(B) Colorimetric Measurements

Samples of the above films are irradiated for 90 seconds with a light source containing BLB lamps, with an irradiance of about 9 mw/cm². Reflectance measurements are made on the films prior to exposure, immediately after exposure, 2 hours after exposure and 67 hours later. Reflectance readings are made with the film over a black tile, using a Photomatch® 300 colorimeter; the readings are ΔL (lighter/darker), Δa (redder/greener) and Δb (yellow/bluer). The values for ΔE set forth in Table 12 below are derived from the square root of the sum of the squares ($\Delta L^2 + \Delta a^2 + \Delta b^2$) and give an approximation of the overall change of color of the film sample. It is observed that the control hexaphenylbiimidazoles form relatively little color after exposure which disappeared after 2 hours. All film samples of this invention retained color longer. This confirms that the hexaphenylbiimidazole compounds of this invention have longer radical life.

TABLE 12

Change in ΔE Values

	Film Sample (see Tables 5 and 6)	Before Exposure	After Exposure	2 Hrs. After Exposure	67 Hrs. After Exposure
5					
10	1	1.5	6.2	5.1	5.1
	2	1.3	5.0	3.3	3.1
15	3	0.6	5.0	2.3	1.8
	4	1.4	6.1	4.4	4.4
	5	1.6	5.7	3.7	2.8
20	6	1.7	3.1	2.6	2.6
	7	1.8	5.2	3.3	2.8
25	8	1.6	5.3	4.3	4.3
	9	1.5	5.1	3.5	3.5
	10	1.3	6.0	4.7	4.7
30	Control 1, Example 11	1.1	1.9	1.1	—
35	Control 2, Example 11	1.5	2.3	1.0	—

(C) Radical Recombination By Heating

A 15% solution of hexaphenylbiimidazole No. 3, Example 11, in methylene chloride is spotted on filter paper, and after color formation by ultraviolet irradiation, a portion of the colored pattern is placed

40 in an oven set at 85—90°C.

Initially, before exposure, optical density is 0.38; after a 90 second exposure the optical density is 1.40.

	Time	Room Temp. (O.D.)	Oven Heated (O.D.)
45	1 hour	1.37	1.13
	1.75 hours	1.34	1.06
50	2 hours	1.33	1.02
	20 hours	1.20	0.64
55	44 hours	1.16	0.56

This shows that the radicals formed by the exposure to ultraviolet light can be made to recombine at elevated temperatures over an extended period. Reexposure of the heated sample to ultraviolet light

60

Claims


1. Photoimaging composition comprising an admixture of

(A) 2,4,5-triphenylimidazolyl dimer; and at least one compound taken from group consisting of

65

(B1) a leuco dye that is oxidizable to dye by the imidazolyl radicals; and

(B2) an addition polymerizable ethylenically unsaturated monomeric compound, characterized in that dimer (A) is of the formula



wherein

R₁ is 2-bromo, 2-chloro, 2-fluoro 2-alkyl of 1 to 4 carbon atoms and 2,4-dichloro;

R₂ is 2-bromo, 2-chloro, 2-fluoro, 4-chloro, 2-alkyl of 1 to 4 carbon atoms, 2-cyano, and 2-alkoxy wherein the alkyl radical is 1 to 4 carbon atoms; and

R₃ is 3,4-dimethoxy, 3,4-diethoxy, 2,3-dimethoxy, 2,4,6-trimethoxy, 4-alkoxy wherein the alkyl radical is of 1 to 4 carbon atoms and 3,4-methylenedioxy; the imidazolyl dimer having an extinction coefficient determined in methylene chloride at 10⁻⁵ to 10⁻³ mol/liter at 350 nm of the least 4000 liters/mol cm and at 400 nm of at least 250 liters/mol cm.


2. A photoimaging composition according to Claim 1 characterized in that there is present at least one leuco dye which has one to two removable hydrogens, the removal of which forms a differently colored compound, with the proviso that when the leuco form has only one removable hydrogen and the resultant dye is cationic, there is also present a mineral acid, organic acid or acid-supplying compound which forms a salt with the leuco form of the dye.

3. A photoimaging composition according to Claim 2 characterized in that the leuco dye is the salt of an acid in leuco form of a triphenylmethane dye having, in at least two of the phenyl rings positioned para to the methane carbon atom, a substituent selected from the group consisting of amino, and C₁ to C₄ dialkyl amino groups, the acid being a mineral acid, an organic acid, or an acid-supplying compound.

4. A photoimaging composition according to Claim 2 or Claim 3 characterized in that (C) a redox couple of a photoactivatable oxidant component and a reductant component is present in the admixture.

5. A photoimaging composition according to Claim 4 characterized in that the photoactivatable oxidant component is a polynuclear quinone absorbing principally in the 430 nm to 550 nm region.

6. A photoimaging composition according to Claim 4 or Claim 5 characterized in that the reductant component is an acyl ester of triethanolamine of the formula



where R is alkyl of 1 to 4 carbon atoms.

7. A photoimaging composition according to any one of Claims 1 to 6 characterized in that (D) a film-forming polymeric binder is present.

8. A photoimaging composition according to Claim 7 characterized in that the polymeric binder is cellulose acetate butyrate.

9. A photoimaging composition according to any one of claims 1 to 8 characterized in that the 2,4,5-triarylimidazolyl compound is 2,2',4,4'-tetrakis(o-chloro-phenyl)-5,5'-bis-(m,p-dimethoxy-phenyl)-biimidazole dimer.

10. A photopolymerizable composition according to Claim 1 characterized in that there is present at least one addition polymerizable ethylenically unsaturated compound (B2) having at least one polymerizable ethylenic group.

11. A photopolymerizable composition according to Claim 10 characterized in that (C) at least one agent selected from the group consisting of a free radical producing hydrogen donor agent and an active methylene compound is present.

12. A photopolymerizable composition according to Claim 11 characterized in that the agent is a leuco dye.

13. A photopolymerizable composition according to any one of Claims 10 to 12 characterized in that (D) a film-forming polymeric binder is present.

14. A photopolymerizable composition according to Claim 13 characterized in that the polymeric binder is a methyl methacrylate containing polymer or copolymer.

5 15. A photopolymerizable composition according to any one of claims 10 to 14 characterized in that (E) a chain transfer agent is present.

16. A photopolymerizable composition according to Claim 15 characterized in that the chain transfer agent is 2-mercaptobenzothiazole.

10 17. A photopolymerizable composition according to any one of Claims 10 to 16 characterized in that the 2,4,5-triarylimidazolyl compound is 2,2',4,4'-tetrakis(o-chloro-phenyl)-5,5'-bis-(m,p-dimethoxyphenyl)-biimidazole dimer.


Revendications

15 1. Composition photographique comprenant un mélange de:

(A) un dimère de 2,4,5-triphénylimidazole; et au moins un composé pris dans le group constitué par

(B1) un colorant leuco qui est oxydable en colorant par les radicaux imidazole; et

20 (B2) un composé monomère éthyléniquement insaturé polymérisable par addition, caractérisé en ce que le dimère (A) est de la formule:



40 dans laquelle

R₁ est un substituant 2-bromo, 2-fluoro, 2-alcoyle de 1 à 4 atomes de carbone ou 2,4-dichloro;

R₂ est un substituant 2-bromo, 2-chloro, 2-fluoro, 4-chloro, 2-alcoyle de 1 à 4 atomes de carbone, 2-cyano ou 2-alcoyloxy où le radical alcoyle a de 1 à 4 atomes de carbone, et

45 R₃ est un substituant 3,4-diméthoxy, 3,4-diéthoxy, 2,3-diméthoxy, 2,4,6-triméthoxy, 4-alcoyloxy où le radical alcoyle a de 1 à 4 atomes de carbone ou 3,4-méthylènedioxy, le dimère d'imidazole ayant un coefficient d'extinction déterminé dans le chlorure de méthylène à une concentration de 10⁻⁵ à 10⁻³ mole/litre à 350 nm d'au moins 4000 litres/mole-cm et à 400 nm d'au moins 250 litres/mole-cm.


2. Une composition photographique selon la revendication 1, caractérisée en ce qu'est présent au moins un colorant leuco qui a un ou deux hydrogènes enlevables, dont l'enlèvement forme un composé de couleur différente, avec la condition que quand la forme leuco a seulement un hydrogène enlevable et que le colorant résultant est cationique, est présent aussi un acide minéral, un acide organique ou un composé fournissant un acide qui forme un sel avec la forme leuco du colorant.

3. Une composition photographique selon la revendication 2, caractérisée en ce que le colorant leuco est le sel d'un acide dans la forme leuco d'un colorant de triphénylméthane ayant, dans au moins deux des noyaux phényle en position para par rapport à l'atome de carbone du méthane, un substituant choisi parmi le groupe amino et les groupes di(alcoyle en C₁ à C₄) amino, l'acide étant un acide minéral, un acide organique ou un composé fournissant un acide.

4. Une composition photographique selon la revendication 2 ou la revendication 3, caractérisée en ce que (C) un couple redox d'un constituant oxydant photoactivable et d'un constituant réducteur est présent dans le mélange.

5. Une composition photographique selon la revendication 4, caractérisée en ce que le constituant oxydant photoactivable est une quinone polynucléaire absorbant principalement dans la région de 430 nm à 550 nm.

6. Une composition photographique selon la revendication 4 ou la revendication 5, caractérisée en ce que le constituant réducteur est un ester d'acyl de triéthanolamine de la formule



5 dans laquelle R est un groupe alcoyle de 1 à 4 atomes de carbone.

7. Une composition photographique selon l'une quelconque des revendications 1 à 6, caractérisée en ce que (D) un liant polymère filmogène est présent.

8. Une composition photographique selon la revendication 7, caractérisée en ce que le liant polymère est de l'acétobutyrate de cellulose.

10 9. Une composition photographique selon l'une quelconque des revendications 1 à 8, caractérisée en ce que le composé de 2,4,5-triarylimidazolyle est le dimère de 2,2',4,4'-tétrakis(o-chloro-phényl)-5,5'-bis-(m,p-diméthoxyphényl)-biimidazole.

10. Une composition photopolymérisable selon la revendication 1, caractérisée en ce qu'est présent au moins un composé éthyléniquement insaturé polymérisable par addition (B2) ayant au
15 moins un groupe éthylénique polymérisable.

11. Une composition photopolymérisable selon la revendication 10, caractérisée en ce que (C) au moins un agent choisi dans le groupe consistant en un agent donneur d'hydrogène produisant des radicaux libres et un dérivé de méthylène actif est présent.

12. Une composition photopolymérisable selon la revendication 11, caractérisée en ce que l'agent
20 est un colorant leuco.

13. Une composition photopolymérisable selon l'une quelconque des revendications 10 à 12, caractérisée en ce que (D) un liant polymère filmogène est présent.

14. Une composition photopolymérisable selon la revendication 13, caractérisée en ce que le liant polymère est un polymère ou copolymère contenant du méthacrylate de méthyle.

25 15. Une composition photopolymérisable selon l'une quelconque des revendications 10 à 14, caractérisée en ce que (E) un agent de transfert de chaîne est présent.

16. Une composition photopolymérisable selon la revendication 15, caractérisée en ce que l'agent de transfert de chaîne est du 2-mercaptobenzothiazole.


17. Une composition photopolymérisable selon l'une quelconque des revendications 10 à 16,
30 caractérisée en ce que le composé de 2,4,5-triarylimidazolyle est le dimère de 2,2',4,4'-tétrakis(o-chloro-phényl)-5,5'-bis(m,p-diméthoxyphényl)-biimidazole.

Patentansprüche

35 1. Photoabbildende Zusammensetzung, umfassend eine Mischung aus
(A) einem 2,4,5-Triphenylimidazol-Dimeren; und wenigstens eine Verbindung aus der Gruppe bestehend aus

(B1) einem Leukofarbstoff, der durch die Imidazolyl-Radikale zu einem Farbstoff oxydierbar ist; und

40 (B2) einer additionspolymerisierbaren, ethylenisch ungesättigten monomeren Verbindung, dadurch gekennzeichnet, daß das Dimer (A) die Formel



60 besitzt, in der

R₁ 2-Bromo, 2-Chloro, 2-Fluoro, 2-Alkyl mit 1 bis 4 Kohlenstoff-Atomen und 2,4-Dichloro ist,
R₂ 2-Bromo, 2-Chloro, 2-Fluoro, 4-Chloro, 2-Alkyl mit 1 bis 4 Kohlenstoff-Atomen, 2-Cyano und 2-Alkoxy ist, worin der Alkyl-Rest ein solch r mit 1 bis 4 Kohlenstoff-Atomen ist,

65 R₃ 3,4-Dimethoxy, 3,4-Diethoxy, 2,3-Dimethoxy, 2,4,6-Trimethoxy, 4-Alkoxy-, worin der Alkyl-Rest ein solcher mit 1 bis 4 Kohlenstoff-Atomen ist, und 3,4-Methylenedioxy ist, wobei das Imidazolyl-

Dimer einen Extinktionskoeffizient, bestimmt in Methylenchlorid bei 10^{-5} bis 10^{-3} mol/l, bei 350 nm von wenigstens 4000 l/mol.cm und bei 400 nm von wenigstens 250 l/mol.cm besitzt.

2. Photoabbildende Zusammensetzung nach Anspruch 1, dadurch gekennzeichnet, daß wenigstens ein Leukofarbstoff vorliegt, der einen oder zwei entfernbare Wasserstoffe besitzt, bei deren Entfernung eine unterschiedlich gefärbte Verbindung gebildet wird, mit der Maßgabe, daß in dem Fall, in dem die Leuko-Form nur einen entfernbaren Wasserstoff besitzt und der resultierende Farbstoff kationisch ist, auch eine Mineralsäure, organische Säure oder säureliefernde Verbindung anwesend ist, die ein Salz mit der Leuko-Form des Farbstoffs bildet.

3. Photoabbildende Zusammensetzung nach Anspruch 2, dadurch gekennzeichnet, daß der Leukofarbstoff das Salz einer Säure in der Leuko-Form eines Triphenylmethanfarbstoffs ist, der in wenigstens zweien der Phenyl-Ringe in der p-Stellung zu dem Methan-Kohlenstoff-Atom einen Substituenten ausgewählt aus der aus Amino und C_1 - bis C_4 -Dialkylamino-Gruppen bestehenden Gruppe besitzt, wobei die Säure eine Mineralsäure, organische Säure oder säureliefernde Verbindung ist.

4. Photoabbildende Zusammensetzung nach Anspruch 2 oder Anspruch 3, dadurch gekennzeichnet, daß (C) ein Redox Paar aus einer photoaktivierbaren Oxidationsmittel-Komponente und einer Reduktionsmittel-Komponente in der Mischung vorhanden ist.

5. Photoabbildende Zusammensetzung nach Anspruch 4, dadurch gekennzeichnet, daß die photoaktivierbare Oxidationsmittel-Komponente ein mehrkerniges Chinon ist, das hauptsächlich in dem Bereich von 430 nm bis 550 nm absorbiert.

6. Photoabbildende Zusammensetzung nach Anspruch 4 oder Anspruch 5, dadurch gekennzeichnet, daß die Reduktionsmittel-Komponente ein Acylester des Triethanolamins der Formel



ist, in der R ein Alkyl mit 1 bis 4 Kohlenstoff-Atomen ist.

7. Photoabbildende Zusammensetzung nach einem der Ansprüche 1 bis 6, dadurch gekennzeichnet, daß (D) ein filmbildendes polymeres Bindemittel anwesend ist.

8. Photoabbildende Zusammensetzung nach Anspruch 7, dadurch gekennzeichnet, daß das polymere Bindemittel Celluloseacetat-butyrat ist.

9. Photoabbildende Zusammensetzung nach einem der Ansprüche 1 bis 8, dadurch gekennzeichnet, daß die 2,4,5-Triarylimidazolyl-Verbindung das 2,2',4,4'-Tetrakis(o-chlorophenyl)-5,5'-bis(m,p-dimethoxyphenyl)-biimidazol-Dimer ist.

10. Photopolymerisierbare Zusammensetzung nach Anspruch 1, dadurch gekennzeichnet, daß wenigstens eine additionspolymerisierbare, ethylenisch ungesättigte Verbindung (B2) mit wenigstens einer polymerisierbaren ethylenischen Gruppe vorliegt.

11. Photopolymerisierbare Zusammensetzung nach Anspruch 10, dadurch gekennzeichnet, daß (C) wenigstens ein Mittel ausgewählt aus der aus freie Radikale bildenden Wasserstoff-Donator-Agentien und einer aktiven Methylen-Verbindung bestehenden Gruppe anwesend ist.

12. Photopolymerisierbare Zusammensetzung nach Anspruch 11, dadurch gekennzeichnet, daß das Mittel ein Leuko-Farbstoff ist.

13. Photopolymerisierbare Zusammensetzung nach einem der Ansprüche 10 bis 12, dadurch gekennzeichnet, daß (D) ein filmbildendes polymeres Bindemittel anwesend ist.

14. Photopolymerisierbare Zusammensetzung nach Anspruch 13, dadurch gekennzeichnet, daß das polymere Bindemittel ein Methylmethacrylat enthaltendes Polymerisat oder Copolymerisat ist.

15. Photopolymerisierbare Zusammensetzung nach einem der Ansprüche 10 bis 14, dadurch gekennzeichnet, daß (E) ein kettenübertragendes Mittel anwesend ist.

16. Photopolymerisierbare Zusammensetzung nach Anspruch 15, dadurch gekennzeichnet, daß das kettenübertragende Mittel 2-Mercaptobenzthiazol ist.

17. Photopolymerisierbare Zusammensetzung nach einem der Ansprüche 10 bis 16, dadurch gekennzeichnet, daß die 2,4,5-Triarylimidazolyl-Verbindung 2,2',4,4'-Tetrakis(o-chlorophenyl)-5,5'-bis(m,p-dimethoxyphenyl)-biimidazol-Dimer ist.